

PO Box 1751  
Adelaide SA 5001

250 Victoria Square/  
Tamtanyangga  
Adelaide SA 5000

Tel : 1300 653 366  
Fax : 1300 883 171

Internet : [www.awqc.com.au](http://www.awqc.com.au)  
Email : [awqc@sawater.com.au](mailto:awqc@sawater.com.au)



Arad Ltd  
Attn: Michaela Avraham  
Kibbutz Dalia

19239  
ISRAEL

11/04/2014

Dear Michaela,

Please find the attached report to AS/NZS 4020:2005 for Water Meter - Plastic Body OCTAVE (1½ Representative) submitted for testing.

Should you have any enquiries about the report or any other matters pertaining to the Standard please contact the laboratory on 61 8 7424 1512

Yours sincerely,

A handwritten signature in blue ink, appearing to read "Peter Christopoulos", is written over a light blue horizontal line.

Peter Christopoulos  
Snr Technical Officer Micro



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025



## FINAL REPORT

Report ID : 136008

### Report Information

**Submitting Organisation :** 00121312 : Arad Ltd  
**Account :** 142320 : Arad Ltd  
**AWQC Reference :** 142320-2013-CSR-2 : Prod Test: Plastic Body Water Meter  
**Project Reference :** PT-2277  
**Product Designation :** Water Meter - Plastic Body OCTAVE (1"½ Representative)  
**Composition of Product :** Polyamide Polymer Body (see attachment 1 for further information).  
**Product Manufacturer :** Arad Ltd., Kibbutz Dalia, ISRAEL.  
**Use of Product :** In-Line/ Water Meter.  
**Sample Selection:** As provided by the submitting organisation.  
**Testing Requested :** **AS/NZS 4020:2005 TESTING OF PRODUCTS FOR USE IN CONTACT WITH DRINKING WATER**  
**Product Type :** Composite  
**Samples :** Samples were prepared and controlled as described in Appendix A of AS/NZS 4020:2005  
**Extracts :** Extracts were prepared as described in Appendix C, D, E, F, G, H.  
**Project Completion Date :** 11-Apr-2014  
**Project Comment :** The results presented herein demonstrate compliance of Water Meter - Plastic Body OCTAVE (1"½ Representative Model) to AS/NZS 4020 when tested at the 'in-the-product' exposure with a 0.1 scaling factor at 20°C ± 2°C. Product range to include 1"½ to 12".

PLEASE NOTE THAT THIS REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL

THE RESULTS STATED IN THIS REPORT RELATE TO THE SAMPLE OF THE PRODUCT SUBMITTED FOR TESTING. ANY CHANGES IN THE MATERIAL FORMULATION, PROCESS OF MANUFACTURE, THE METHOD OF APPLICATION, OR THE SURFACE AREA-TO-VOLUME RATIO IN THE END USE, COULD AFFECT THE SUITABILITY OF THE PRODUCT FOR USE IN CONTACT WITH DRINKING WATER



Michael Glasson  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025

## FINAL REPORT

Report ID : 136008

### Summary of Results

APPENDIX	RESULTS
C – Taste of Water Extract	Passed at the in-the-product exposure with a scaling factor of 0.1 applied.
D – Appearance of Water Extract	Passed at the in-the-product exposure with a scaling factor of 0.1 applied.
E – Growth of Aquatic Micro-organisms	Passed when tested at the in-use exposure.
F – Cytotoxic Activity of Water Extract	Passed at the in-the-product exposure with a scaling factor of 0.1 applied.
G – Mutagenic Activity of Water Extract	Passed at the in-the-product exposure with a scaling factor of 0.1 applied.
H – Extraction of Metals	Passed at the in-the-product exposure with a scaling factor of 0.1 applied.

### Test Methods

Test(s) in Appendix	AWQC Test Method	Reference Method
C	T0320-01	AS/NZS 4020:2005
D	TO029-01 & TO018-01	APHA 2130b
E	TO014-03	APHA 4500 O C
F	TM-001	AS/NZS 4020:2005
G	TM-002	AS/NZS 4020:2005
H	TIC-006	EPA 200.8

Summary Comment : Not applicable.

## FINAL REPORT

Report ID : 136008

### CLAUSE 6.2 Taste of Water Extract

**Sample Description** The meter was tested at the in-the-product exposure. Each meter held approximately 220 mL of water. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

**Extraction Temperature** 20°C ± 2°C.

**Test Method** Taste of Water Extract (Appendix C)

**Test Information**

**Scaling Factor** A scaling factor of 0.1 was applied.

**Results** Not detected.

**Evaluation** The product passed the requirements of clause 6.2 when tested at the in-the-product exposure with a scaling factor of 0.1 applied.

**Number of Samples** 2.

**Test Comment** Not applicable.



Peter Christopoulos  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025

## FINAL REPORT

Report ID : 136008

### CLAUSE 6.3 Appearance of Water Extract

**Sample Description** The meter was tested at the in-the-product exposure. Each meter held approximately 220 mL of water. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

**Extraction Temperature** 20°C ± 2°C.

**Test Method** Appearance of Water Extract (Appendix D)

**Scaling Factor** A scaling factor of 0.1 was applied.

#### Results

	<u>Test (- Blank)</u>	<u>Maximum Allowed</u>	<u>Units</u>
Colour	<1	5	HU
Turbidity	<0.1	0.5	NTU

**Evaluation** The product passed the requirements of clause 6.3 when tested at the in-the-product exposure with a scaling factor of 0.1 applied.

**Number of Samples** 1.

**Test Comment** Not applicable.



Joanne Clark  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025

WORLD RECOGNISED  
ACCREDITATION

## FINAL REPORT

Report ID : 136008

### CLAUSE 6.4 Growth of Aquatic Micro-organisms

**Sample Description** The non-metallic components were immersed at the in-use exposure. The surface area was in the range 1000 mm<sup>2</sup> per Litre and 15,000 mm<sup>2</sup> per Litre. Extracts were prepared using 1000 mL volumes of test water.

**Test Method** Growth of Aquatic Micro-organisms (Appendix E)

**Inoculum** The volume of the inoculum was 100 mL

**Scaling Factor** Not applicable.

Results			
Mean Dissolved Oxygen	Control		7.2 mg/L
Mean Dissolved Oxygen Difference	Positive Reference		5.4 mg/L
	Negative Reference		<0.1 mg/L
	Test		<0.10 mg/L

**Evaluation** The product passed the requirements of clause 6.4 when tested at the in-use exposure.

**Number of Samples** 1.

**Test Comment** Not applicable.



Stephanie Semczuk  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025

## FINAL REPORT

Report ID : 136008

### CLAUSE 6.5 Cytotoxic Activity of Water Extract

<b>Sample Description</b>	The meter was tested at the in-the-product exposure. Each meter held approximately 220 mL of water. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.
<b>Extraction Temperature</b>	20°C ± 2°C.
<b>Test Method</b>	Cytotoxic Activity of Water Extract (Appendix F)
<b>Scaling Factor</b>	A scaling factor of 0.1 was applied.
<b>Results</b>	Non Cytotoxic.
<b>Evaluation</b>	The product passed the requirements of clause 6.5 when tested at the in-the-product exposure with a scaling factor of 0.1 applied.
<b>Number of Samples</b>	1.
<b>Test Comment</b>	The test extracts and blank extracts were used to prepare nutrient growth medium and subsequently used to grow a cell line (ATCC Number CCL 81) in the analysis. In addition zinc sulphate (0.4 mmol) was used for the positive control in the analysis.



Brendon King  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025



## FINAL REPORT

Report ID : 136008

### CLAUSE 6.6 Mutagenic Activity of Water Extract

**Sample Description** The meter was tested at the in-the-product exposure. Each meter held approximately 220 mL of water. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

**Extraction Temperature** 20°C ± 2°C.

**Test Method** Mutagenic Activity of Water Extract (Appendix G)

**Scaling Factor** A scaling factor of 0.1 was applied.

#### Results

	<u>Bacteria Strain</u>		<u>Number of Revertants per Plate</u>			
	S9	Blank	Sample Extract	Positive Controls		
<i>Salmonella typhimurium</i> TA98	-	22, 34, 18	11, 18, 17	2069, 2287, 1975		<u>NPD</u> (20µg)
Mean ± Standard deviation		24.7 ± 8.3	15.3 ± 3.8	2110.3 ± 160.1		
	+	24, 29, 30	16, 15, 13	2528, 2303, 2962		<u>2-AF</u> (20µg)
Mean ± Standard deviation		27.7 ± 3.2	14.7 ± 1.5	2597.7 ± 335.0		
<i>Salmonella typhimurium</i> TA100	-	495, 499, 558	575, 511, 506	803, 897, 995		<u>Azide</u> (1.0µg)
Mean ± Standard deviation		517.3 ± 35.3	530.7 ± 38.5	898.3 ± 96.0		
	+	221, 257, 255	235, 189, 215	2582, 2532, 2495		<u>2-AF</u> (20µg)
Mean ± Standard deviation		244.3 ± 20.2	213.0 ± 23.1	2536.3 ± 43.7		
<i>Salmonella typhimurium</i> TA102	-	634, 633, 641	556, 601, 651	2769, 2875, 2745		<u>Mitomycin C</u> (10µg)
Mean ± Standard deviation		636.0 ± 4.4	602.7 ± 47.5	2796.3 ± 69.2		
	+	582, 616, 711	630, 551, 551			
Mean ± Standard deviation		636.3 ± 66.9	577.3 ± 45.6			

**Comments** S9 was used as a metabolic activator. NPD (4-nitro-o-phenylenediamine), Azide, and Mitomycin C are specific positive controls for strains TA98, TA100 and TA102 respectively while 2 - AF (2-aminofluorene) when used in conjunction with S9 is a positive control for both TA98 and TA100

**Evaluation** The product passed the requirements of clause 6.6 when tested at the in-the-product exposure with a scaling factor of 0.1 applied.

**Number of Samples** 1.

**Test Comment** Not applicable.



Peter Christopoulos  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025

## FINAL REPORT

Report ID : 136008

### CLAUSE 6.7 Extraction of Metals

**Sample Description** The meter was tested at the in-the-product exposure. Each meter held approximately 220 mL of water. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

**Extraction Temperature** 20°C ± 2°C.

**Test Method** Extraction of Metals (Appendix H)

**Scaling Factor** A scaling factor of 0.1 was applied.

**Method of Analysis** All methods used to determine concentrations of metals are based on those described in the 21st edition of Standard Methods for the Examination of Water and Wastewater published by the APHA, AWWA and WEF (2005). The methods have been adapted for the instrumentation in use at the Australian Water Quality Centre.  
Concentration of the metals described in Table 2 of the AS/NZS 4020:2005 are determined as follows:  
Antimony, Arsenic, Barium, Cadmium, Chromium, Copper, Lead, Mercury, Molybdenum, Nickel, Selenium and Silver by Inductively Coupled Plasma Mass Spectrometry.

Results	Limit of Reporting mg/L	Blank mg/L	Test 1 mg/L	Test 2 mg/L	Max Allowed mg/L
<b>Final Extract</b>					
Antimony	0.0005	<0.0005	<0.0005	<0.0005	0.003
Arsenic	0.0003	<0.0003	<0.0003	<0.0003	0.007
Barium	0.0005	<0.0005	<0.0005	<0.0005	0.7
Cadmium	0.0001	<0.0001	<0.0001	<0.0001	0.002
Chromium	0.0001	<0.0001	<0.0001	<0.0001	0.05
Copper	0.0001	<0.0001	0.0002	0.0002	2.0
Lead	0.0001	<0.0001	<0.0001	<0.0001	0.01
Mercury	0.00003	<0.00003	<0.00003	<0.00003	0.001
Molybdenum	0.0001	<0.0001	<0.0001	<0.0001	0.05
Nickel	0.0001	<0.0001	<0.0001	0.0001	0.02
Selenium	0.0001	<0.0001	<0.0001	<0.0001	0.01
Silver	0.00003	<0.00003	0.00004	0.00003	0.1

**Evaluation** The product passed the requirements of clause 6.7 when tested at the in-the-product exposure with a scaling factor of 0.1 applied.

**Number of Samples** 1.

**Test Comment** Not applicable.



Dzung Bui  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025

**AS/NZS 4020:2005****Attachment 1**

**REPORT NUMBER** 136008  
**SAMPLE REFERENCE** PT-2277  
**DATE** 11/04/2014

<b>A. MATERIAL</b>		<b>B. COMPONENTS</b>		<b>C. FITTINGS/ASSEMBLED PRODUCT</b>	
Name & Code	Manufacturer/ Supplier	Name & Code	Manufacturer/ Supplier	Name & Code	Manufacturer/ Supplier
VICTREX PEEK 450G BEIGE	VICTREX	96210209 D-FLOW SENSOR WIRE L=260mm	D-FLOW	Octave 1 1/2"-2"	ARAD Ltd.
29403603 PPO +30% GF (GFN 1630V- 73701(BLACK))	SUKEET (SABIC)	26353109 (exist only in 2" w/m) INLET FLOW TUBE OCTAVE 2	ARAD Ltd.		
29403603 PPO +30% GF (GFN 1630V- 73701(BLACK))	SUKEET (SABIC)	26353309 (exist only in 3" w/m) INLET FLOW TUBE OCTAVE 2	ARAD Ltd.		
29403603 PPO +30% GF (GFN 1630V- 73701(BLACK))	SUKEET (SABIC)	24630009 (exist only in 4" w/m) FLOW STRAIGHTNER OCTAVE 4	ARAD Ltd.		
29813006 SILICONE SEALANT (DC CLEAR 781,CLEAR SILICONE SEALANT)	DOW CORNING EUROPE SA				
29100013EM PPA+40%GF (GRIVORY XE 4101 BLACK 9225)	EMS CHEMIE AG	31535009 (exist only in 1 1/2" w/m) BODY OCTAVE 1 1/2" PLASTIC THREADED	ARAD Ltd.		
29100013EM PPA+40%GF (GRIVORY XE 4101 BLACK 9225)	EMS CHEMIE AG	31540009(exist only in 2" w/m) BODY OCTAVE 2" PLASTIC THREADED	ARAD Ltd.		

